


BRIEF EVALUATION REPORT


BS: 476-Part 5: Ignitability Evaluation for Materials

| | | |
|---|---|---|
| Date of Evaluation | : | May 07, 2015 |
| Sponsor | : | M/s Shahsahib Wood Wool Enterprises 583, Mukherjee Nagar, New Delhi - 110 009 |
| Description of Product | : | ACUTEX WOODWOOL ACOUSTIC BOARD Thickness: 25 mm, Nominal Bulk Density: 400 kg/m ³ (Product description has been prepared on the basis of the information provided by the sponsor). |
| Specimen dimensions | : | 228 mm x 228 mm x 25 mm |
| Results | | |
| Duration of exposure to specified flame | : | 10 sec. |
| Duration of flaming after removal of specified flame | : | NIL |
| Time for burning to reach the edge of specimen | : | Not applicable |
| Extent of burning of specimen within 20 sec. | : | NIL |
| Classification | : | ' P ' Not Easily Ignitable |

The evaluation results relate only to the behaviour of the specimens of a product under the particular condition of the evaluation, they are not intended to be the sole criterion for assessing the potential hazard of the material in use.

This report is valid for three years from the date of evaluations of the product.


(RAKESH KUMAR)
CO-INVESTIGATOR


(A. A. ANSARI)
PRINCIPAL INVESTIGATOR



FIRE RESEARCH LABORATORY
CSIR - Central Building Research Institute
Roorkee - 247 667 (U.K.) INDIA

